

Product Information



Lithography

FEATURES

- E-beam patternable
- Negative tone
- Etch resistance
- High purity

BENEFITS

- Direct write
- Thin films
- High resolution
- Excellent line edge roughness
- Aqueous development

APPLICATION METHODS

- Standard spin-on deposition coating equipment.
- Typical spin-coating speeds between 1000 to 5000 rpm's.
- Hot plate exposure of 150 °C can be used to remove the solvent.

Dow Corning[®] XR-1541 E-Beam Resist

Hydrogen silsesquioxane electron beam spin-on resist

TYPICAL PROPERTIES

Specification Writers: Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Property	Unit	Value
Minimal Feature Size	nm	6
Shelf Life at 5°C	months	6
Edge Definition	nm	3.3
Refractive Index	-	1.41
Trace Metals Impurities	ppb	<10
Spin-on Film Thickness - 2%	nm	30 - 60
Spin-on Film Thickness - 4%	nm	55 - 115
Spin-on Film Thickness - 6%	nm	85 - 180

DESCRIPTION

Dow Corning XR-1541 E-Beam Resists are comprised of hydrogen silsesquioxane (HSQ) resin in a carrier solvent of methylisobutylketone (MIBK). It functions as a negative tone electron-beam resist with capability to define features as small as 6 nm. These resists are processed to high purity semiconductor grade (<10 ppb trace metals). They are available in compositions of resin in carrier solvent to produce thin films ranging in thickness of 30 to 180 nm in a single coat. Customized compositions are available upon request. Formulation with a volatile methyl siloxane (VMS) fluid blend carrier solvent is also available upon request. The VMS blend carrier solvent is exempt from United States federal and state regulations covering volatile organic compounds (VOC). High purity semiconductor grade MIBK and siloxane rinse solvents are available from Dow Corning as companion products. The line rinse solvents conform to the same purity specifications as the XR-1541 resist products.

PROCESSING/CURING

Variable energy electron beam lithography allows control of the electron penetration depth in HSQ from below 35 nm to greater than 175 nm with a single exposure tool with beam energies from 200 eV to 100 keV. Optimal doses depend upon beam energy, desired resolution, and film thickness, but area doses from 400 to 700 $\mu\text{C}/\text{cm}^2$ are typical and dependent on thickness. A 350 °C post exposure bake in N₂ enhances the contrast properties of the film. Films can then be developed in a standard aqueous base developer (0.26 N TMAH).

PACKAGING

Dow Corning® XR-1541 E-Beam Resists is available in 125-ml, and 250-ml containers

STORAGE AND SHELF LIFE

Refer to the Sales Specifications and/or Product Label for these products. These products have a shelf life of 6 months from date of manufacture.

PRODUCT LEVEL DESCRIPTION

Dow Corning E-beam Resists are formulated to directly write fine patterns with high resolution. Applications for the photoresists are for mask making and for next generation lithography processing.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area. For further information, please see our website, www.dowcorning.com, or consult your local Dow Corning representative.

LIMITATIONS

These products are neither tested nor represented as suitable for medical or pharmaceutical uses.

LIMITED WARRANTY INFORMATION PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken

as inducements to infringe any patent. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

SAFE HANDLING INFORMATION

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT WWW.DOWCORNING.COM, OR FROM YOUR DOW CORNING REPRESENTATIVE, OR DISTRIBUTOR, OR BY CALLING YOUR GLOBAL DOW CORNING CONNECTION.

For More Information

To learn more about these and other products available from Dow Corning, please visit the Dow Corning Electronics website at www.dowcorning.com/electronics.



Electronics
Solutions

Dow Corning and Sylgard are registered trademarks of Dow Corning Corporation. All other trademarks or brand names are the property of their respective owners. ©2008 Dow Corning Corporation. All rights reserved. Printed in USA Form No. 11-1547E-01